



ICS 61.060

WORKING DRAFT EAST AFRICAN STANDARD

General purpose rubber gumboots - specification

EAST AFRICAN COMMUNITY

Copyright notice

This EAC document is copyright-protected by EAC. While the reproduction of this document by participants in the EAC standards development process is permitted without prior permission from EAC, neither this document nor any extract from it may be reproduced, stored or transmitted in any form for any other purpose without prior written permission from EAC.

Requests for permission to reproduce this document for the purpose of selling it should be addressed as shown below or to EAC's member body in the country of the requester:

© East African Community 2023 — All rights reserved East African Community P.O. Box 1096, Arusha Tanzania Tel: + 255 27 2162100 Fax: + 255 27 2162190 E-mail: eac@eachq.org Web: www.eac-quality.net

Reproduction for sales purposes may be subject to royalty payments or a licensing agreement. Violators may be prosecuted.

Contents

Page

Forewo	ord	iv
1	Scope	1
2	Normative references	1
3 4.1 4.2 4.3 4.4 4.5 4.6 4.7 4.8	Terms and definitions	2 Error! Bookmark not defined. Error! Bookmark not defined.
4.9 6	The physical and colourfastness properties	Error! Bookmark not defined.
7	Packing	Error! Bookmark not defined.
Annex A.1 A.2	A (normative) Method for determination of Thermal insulance . Apparatus Procedure	Error! Bookmark not defined. Error! Bookmark not defined. Error! Bookmark not defined.
Annex	B (normative) Determination of mass per unit area	Error! Bookmark not defined.
Annex C.1	C (normative) Warmth-to-mass ratio Procedure	Error! Bookmark not defined. Error! Bookmark not defined.
Annex	D (normative) Permeability of casing fabrics	Error! Bookmark not defined.
Bibliog	raphy	Error! Bookmark not defined.

Foreword

Development of the East African Standards has been necessitated by the need for harmonizing requirements governing quality of products and services in the East African Community. It is envisaged that through harmonized standardization, trade barriers that are encountered when goods and services are exchanged within the Community will be removed.

The Community has established an East African Standards Committee (EASC) mandated to develop and issue East African Standards (EAS). The Committee is composed of representatives of the National Standards Bodies in Partner States, together with the representatives from the public and private sector organizations in the community.

East African Standards are developed through Technical Committees that are representative of key stakeholders including government, academia, consumer groups, private sector and other interested parties. Draft East African Standards are circulated to stakeholders through the National Standards Bodies in the Partner States. The comments received are discussed and incorporated before finalization of standards, in accordance with the Principles and procedures for development of East African Standards.

East African Standards are subject to review, to keep pace with technological advances. Users of the East African Standards are therefore expected to ensure that they always have the latest versions of the standards they are implementing.

The committee responsible for this document is Technical Committee EASC/TC 064, Footwear

Attention is drawn to the possibility that some of the elements of this document may be subject of patent rights. EAC shall not be held responsible for identifying any or all such patent rights.

General purpose rubber gumboots- specification

1 Scope

This Draft East African Standard specifies the requirements, test methods and sampling for general purpose rubber gumboots.

2 Normative references

The following referenced documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 37, Rubber, vulcanized - Determination of tensile stress-strain properties.

ISO 48, Vulcanized rubbers - Determination of hardness (Hardness between 30 and 85 IRHD).

ISO 176, Plastics - Determination of loss of plasticizers - Activated carbon method.

ISO 458-1, Plastics - Determination of stiffness in torsion of flexible materials - Part 1: General method.

ISO/TR 463, Dial gauges reading in 0.01 mm, 0.001 in and 0.000 1 in. ISO 10335, Rubber, and plastics footwear - Nomenclature.

ISO 4643, Moulded plastics footwear — Lined or unlined poly (vinyl chloride) boots for general industrial use — Specification

ISO 5423, Moulded plastics footwear — Lined or unlined polyurethane boots for general industrial use — Specification

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 19952;2005 apply.

4 Requirements

4.1 General Requirements

4.1.1 The lining shall be made of suitable fabric material.

4.1.2 The boots shall be made in sizes 3 to13.

4.1.3 The minimum height of the boot, when measured on the inside at the back of the boot from the insole to the top (see Figure 1), shall be as shown in Table 1.

Table 1. Height of the rubber gumboots, in mm

	MEN'S	WOMEN'S	
Half knee	180-239	153-203	
Short knee	240-329	204-279	
Knee	330-429	280-380	

4.2 Materials

- **4.2.1** Upper materials shall be of rubber conforming to physical requirements given in Table 3.
- **4.2.2** The rubber-mix of the material shall be made of natural rubber, synthetic rubber or a combination of both.



FIG. 1 - RUBBER KNEE BOOTS

4.3 COMPONENTS

4.3.1 Individual components of the rubber gumboots shall comply with the material and thickness requirements prescribed in Table 2.

4.3.2 The rubber components shall comply with the physical requirements prescribed in Table3.

4.4 Weathering Test – All rubber components shall be capable of withstanding ageing in an air-oven at a temperature of 100 ± 1 °C for a period of 24 h according to the procedure given in ISO 1419¹, without developing any brittleness or tackleness.

NOTE: For the purpose of this test, the test pieces may be entire articles or pieces cut from them.

4.5 Leakage Test – On immersion in water, gumboots shall show no sign of leakage in the form of damp patches on the inside surface when in accordance with ISO 20344.

s/n	Boot	Minimum thi	ckness, mm			Test method
	component		,			
	Boot upper	1.5				
1	Foxing				~	
	a) at the heel	4.0				
	b) elsewhere	3.0				
2	Boot bottom	Ove	er cleats		Between	
				cleats		
		Men	Women	Men	Women	
	a) full	12.0	10.0	7.0	5.0	
	thickness					ISO 4643
		8.0	6.0	3.0	2.5	
	b) outsole					
	only					
3	Heel					
	a) full	25.0	20.0	19.0	14.0	
	thickness		4.0		o -	
		9.0	4.0	3.0	2.5	
	b) wearing					
	surface to	Ť				
	Tiller block					

Table 2 - Minimum thickness

1

TABLE 3 –	Physical	requirements	for individual.	rubber	components
	1 Hyoloai	roquironionito	ior manuada,	100001	componionito

	S/N	Characteristic		Requirement			Test method
				Upper	Foxing	Soling	
	i	Relative densit	ty	1.4	1.4	1.5	
	ii	Hardness, IRHD		50-60	50-60	50-70	ISO 48
	iii	Flex resistance No. of cycles, min.	Initial crack	150 000	NA	50 000	ISO 4643
			600 per cent	NA	NA	65 000	
			growin				
	iv	Change in initial hardness after accelerated ageing at 100 ± 10 °C for 24 h, IRHD		+ 8	+ 8	+ 8	ISO 48
				- 0	- 0	- 0	
				C			
	V	Tensile strength, Mpa, min.		7	NA	7	ISO 17706
	vi	Elongation at break, %, min.		300	NA	300	
I							

4.6 FI

FINISH

Rubber boots shall be either matt or gloss finished.

5 Marking

5.1 Rubber gumboot

The rubber gumboot shall be legibly and indelibly marked with the following:

- i) size and fitting number;
- ii) batch number;
- iii) manufacturer's name or registered trade mark and address;
- iv) country of Manufacture/origin.

5.2 Bulk packaging

Each bulk package (bale) shall be legibly and indelibly labelled with the following information:

- a) name of product as "Rubber gumboot";
- b) quantity;
- c) manufacturer or local supplier's name and/or registered trademark and address;
- d) country of manufacture/origin.
- 6 Packaging

The rubber gumboots shall be packed in a suitable material to avoid contamination and damage during transportation and storage.

7 Sampling

Sampling and acceptance criteria should be as given in annex A

Annex A (normative)

Sampling and criteria for conformity

- A.1 **Definitions**
- A.1.1 Lot

All gumboot pairs in a consignment belonging to the same pattern/design and batch of manufacture

A.1.2 Defect

A fault or failure of a gumboot pair to meet the requirements of this standard.

A.1.3 Defective footwear

A gumboot pair with one or more defects as mentioned in this standard.

A.2 Scale of sampling

- A.2.1 Samples shall be selected and examined for each lot separately for ascertaining the conformity of the gumboot to the requirements of this standard.
- A.2.2 Gumboot shall be considered to be of different lots if they differ in shape and design.
- A.2.3 The number of gumboot pairs to be selected from any lot shall depend on the size of the lot and shall be in accordance with Columns 1 and 2 of Table A.1.

A.3 Method of selection

- A.3.1 Gumboot to be selected from the lot shall be chosen at random. To ensure randomness the procedure in A.3.2 shall be used.
- A.3.2 When the gumboot pairs in a lot are not packed in a number of cases (boxes), the sampling shall be as follows:
- Starting from any gumboot pair in the lot, count the pairs as 1,2, etc---up to *r* and so on in one order. Every *r*th pair thus counted shall be withdrawn to constitute a sample (*r* is an integral part of N/n where N is the lot size and n is the sample size). This procedure shall be stopped as soon as the required number of pairs is obtained.
- For example, if a sample of 125 pairs is to be selected from a lot of 3,000 pairs, compute *r* as equal to integral part of 3,000/125=24. Starting from any pair, the footwear shall be counted in one order and every 24th pair shall be withdrawn.
- A.3.3 When the gumboot pairs in a lot are packed in different cases (boxes), a suitable number of boxes (not less than 30 percent of the total boxes in the lot) shall be first chosen at random. For each of the boxes so chosen, an approximately equal number of pairs shall be picked up from its different parts so as to obtain the required number of pairs.
- For example, if a lot consists of 1 000 pairs of gumboot packed in 50 boxes, each containing 20 pairs, choose more than 15 boxes at random. If it is decided to open 20 boxes, then 4 pairs shall be picked up from different parts of each of the 20 boxes to give a total of 80 pairs as specified in Table 1.

No. of gumboot pairs in a lot	Samples for visuall y observ ed defect s (pairs)	Permissible no. of defectiv es (pairs)	Sample size for laboratory testing (pairs)	Permissible no. of defecti ves (pairs)
(1)	(2)	(3)	(4)	(5)
Up to 50	13	0	2	0
51 to100	20	1	3	0
101 to 300	32	1	3	0
301 to 500	50	2	5	1
501 to 1000	80	3	6	1
1001 to 3000	125	5	7	2
3001 and above	200	7	8	3

Table A.1 — Scale of sampling and permissible number of defects

- A.4 All randomly selected gumboot pairs (Table A.1, Column 2) shall be inspected for visually observed defects, i.e.
- i) Difference in shape, design and colour.
- ii) Odd pairing and incorrect size.
- iii) Distorted shapes.
- iv) Faulty jointing and adhesion of sole, heel, toe guard, toe cap and insole.
- v) Finish not even and unpolished.
- A.5 The number of defective gumboots pairs shall not exceed the permissible number given in Table A.1, Column 3. If, however, the number of defective pairs exceeds the permissible number of defectives, the lot shall be rejected.
- A.6 In case the lot has been found satisfactory for visually observed defects, sample pairs for laboratory testing (Table A.1, Column 4) shall be taken from among those drawn (Table A.1, Column 2). The pairs shall be chosen at random and tested for dimensional, physical and chemical characteristics. If the number of defective gumboot pairs is less than or equal to the corresponding permissible number of defectives given in Table A.1, Column 5, the lot shall be declared to have met the requirements of this standard. Otherwise, if the defective gumboot pairs are more than the corresponding permissible number of defectives the lot shall be rejected